



Albi Clad 800
Los Angeles International Airport
Los Angeles, CA
Photo: Timothy Hursley

- Intumescent Fireproofing
- For Exposed Interior & Exterior Structural Steel
- Withstands Severe Weathering and Abuse
- UL Classified for Up to 3 hours

Distributed By:
KBS Passive Fire Pty. Ltd.
Australia - Canada - Saudi Arabia
P: +61 2 9969 7100
F: +61 2 9969 7200
P: +1 604 941 1001
F: +1 604 941 1029
E: mail@kbspassivefire.com
W: www.kbspassivefire.com



DESCRIPTION

Albi Clad 800 intumescent coating is applied to protect both internal and external structural steel, concrete and other construction materials from fire. Its superior resistance to weathering and abuse makes it the universal material for severe environments.

Albi Clad 800 is UL classified for one to three hour protection under E-119 and UL 1709 High Rise, Hydrocarbon fire test criteria. It is available in standard, attractive, white finish.

ALBI CLAD 800 ADVANTAGES

- UL classified for up to 3 hours protection of both interior and exterior steel.
- Lightweight, hammer-hard, thin-film application follows the contour of substrate.
- Outstanding wear resistance eliminates dusting, flaking, cracking and delamination.
- Approved by major building codes and insurance underwriters.
- Outstanding fire protection even after years of extreme exterior weathering, abuse and vibration.
- High resistance to ultraviolet exposure.
- Asbestos-free formulation
- Single-component, factory formulated to eliminate job-site blending.
- Aesthetic, architectural finish



WHERE TO SPECIFY

Specify Albi Clad 800 whenever and wherever you need a dependable, long-lasting exterior fire-resistant coating capable of resisting abrasion, impact, freezing and thawing. Rugged, lightweight and attractive, Albi Clad 800 is optimal for application in a great many commercial, institutional and industrial environments.

PROVEN PERFORMANCE

Tested by Underwriters Laboratories, Inc. and in numerous actual applications, Albi Clad 800 has provided superior performance under a wide range of environmental extremes throughout the world. Even under the most adverse conditions, lightweight Albi Clad 800 maintains long-term protection with outstanding hardness and durability. Its ability to withstand the adverse effects of wind, rain and weather makes Albi Clad 800 the preferred fireproofing material for offshore drilling platforms, petrochemical plants power plants, dock facilities and a range of commercial and industrial applications.

TYPICAL ALBI CLAD 800 UL FIRE-RESISTANCE RATINGS

FIRE TEST ASTM E-119

Typical System	Hourly Rating	Thickness	Design Number	Reinforcement
Column W10 x 49	1	0.25" wft	UL X606	None
	2	0.50" wft	UL X601	Fiberglass ribbon
4" Pipe Column	1	0.38" dft	UL X615	Wire Mesh
	1-1/2	0.61" dft	UL X615	Wire Mesh
	2	0.85" dft	UL X615	Wire Mesh
Beam W8 x 17	1 (Unrestrained)	0.5" wft	UL N601	Fiberglass ribbon
	2 (Restrained)	0.5" wft	UL N601	Fiberglass ribbon

FIRE TEST UL 1709

Column W10 x 49	1	0.25" dft	UL XR607	None
	1-1/2	0.35" dft	UL XR608	Fiberglass ribbon
	2	0.51" dft	UL XR608	Fiberglass ribbon
	2-1/2	0.62" dft	UL XR609	Fiberglass ribbon
	3	0.75" dft	UL XR609	Fiberglass ribbon
8" Pipe	1	0.30" dft	UL XR603	Wire Mesh
	1-1/2	0.58" dft	UL XR603	Wire Mesh
	2	0.98" dft	UL XR603	Wire Mesh

*See Technical bulletin 0788 for complete UL listings.

EASY APPLICATION

For quick, easy installation, Albi Clad 800 is sprayed directly from the shipping container using standard, heavy-duty pneumatic spray equipment. Application may be performed in inclement weather. Application thickness depends on specified fire endurance rating. Albi Clad 800 must be applied by qualified, factory trained people in accordance with the manufacturer's printed instructions and in compliance with specific test specifications. Steel surfaces must be primed with an approved primer before the application of Albi Clad 800.

TYPICAL INSTALLATIONS

- Offshore Drilling Platforms
- Petrochemical Plants
- Power Plants
- Dock Facilities
- Clean Rooms
- Commercial Buildings
- Industrial Sites

PHYSICAL PROPERTIES

Dry Applied Density	68 PCF
Lap Shear	ASTM D1002 – >371 PSI
Bond Strength	ASTM D4541 – >375 PSI
Compressive Strength	ASTM D695 – 2100 PSI
Modulus of Elasticity	ASTM D695 – 94,800 PSI
Flexural Strength	ASTM D790 – 1420 PSI
Modulus of Elasticity	ASTM D790 – 158,000 PSI
Tensile Strength	ASTM D638 – 756 PSI
Abrasion Resistance	ASTM D1044 – 0.40 gm. loss/1000 cycles
Impact Resistance	ASTM D256 – 0.54 ft.lb./in. of notch
Hardness	Shore D – 65 - 70
Weight/Gallon	10.5 ± 0.2 lb.
Coefficient of Thermal Expansion	ASTM D697 – 1.44 x 10 ⁻⁵ in./in./°F
Thermal Conductivity	ASTM F433 – 3.0 BTU in., hr. ft ² °F
Flame Spread	ASTM E84 – 15 (Class A)
Smoke Developed	ASTM E84 – 40 (Class A)
Shelf Life	12 months from date of manufacture if stored between 60° and 90°F under normal warehouse conditions.



Other Albi 800 Literature

- Albi Clad 800 Long Form Guide Specification
- Albi Fireproofing Catalog
- Albi Clad 800 Field Application Manual

Also inquire about these fireproofing products from Albi:

Albi Clad TF

Water-based, thin-film intumescent fireproofing for exposed interior structural steel



Albi DriClad

Low-cost, uniform density mineral board that installs dry year-round



Albi Clad 900

Water-based intumescent fireproofing for exposed interior structural steel



ALBI MANUFACTURING

For more than four decades, American made Albi fireproofing materials have demonstrated superior performance and reliability under a wide range of extreme environments worldwide. These proprietary formulations also meet global building/fire codes and insurance requirements. Lightweight Albi materials provide long-term protection, outstanding durability, aesthetic properties and are completely free from asbestos.



Albi Manufacturing
Division of StanChem, Inc.
 401 Berlin Street
 East Berlin, Connecticut 06023 U.S.A.
 Tel: 860/ 828-0571
 Fax: 860/ 828-3297
<http://www.albi.com>

CITEX Limited¹
 71-75 High Street
 Chislehurst, Kent BR7 5AG
 United Kingdom
 Tel / Fax 44 181 467 2606

¹ A wholly-owned subsidiary of StanChem, Inc.
 11/99